

TEST REPORT

CLIENT:

Company:	Turf and Ivy Solutions	Report Number:	79417
Address:	5 Centerpointe Dr, Ste 400,	Lab Test Number:	3169-2416
	Lake Oswego, Oregon 97035	Test Completion Date:	1/16/2020
		Report Date:	1/18/2020
Requested by:	Patricia Ochoa	Page:	1 of 1

TEST MATERIAL:

Material Type:	Synthetic Turf				Date Red	e Received: 1/13/2020		
Material Condition:	EXCELLENT: XXX GOOD: PO			POOR:		REJECTED:		
Product ID:	Tranquility		_					

TESTING METHODS REQUESTED:

Testing Services Inc. was instructed by the client to test for the following						
Standard: ASTM D1335 Test Method: Standard Test Method for Tuft Bind Strength of Pile Yarn Floorcoverings						

SAMPLING PLAN:

Sampling Date: 1/13/2020

- Specimen sampling is performed in the sampling department at TSI.
- The sampling size of specimens is determined by the test method requirements.
- In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.
- All samples are subjected to the outside environmental conditions of temperature and relative humidly.
- Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.								
None								

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT		
TEST METHOD	TEST DESCRIPTION	IESI RESULI		
ASTM D1335-17e1	Average Tuft Bind Strength	13.1 lbs/force		

Fach individual pull was made from a combination of monofilament and textured fibers, same needle site

Pull #1	12.02 lbs/force	Pull #2	12.59 lbs/force	Pull #3	15.98 lbs/force	Pull #4	12.30 lbs/force	Pull #5	11.90 lbs/force
Pull #6	10.36 lbs/force	Pull #7	14.17 lbs/force	Pull #8	16.05 lbs/force	Pull #9	13.36 lbs/force	Pull #10	12.98 lbs/force
Pull #11	12.69 lbs/force	Pull #12	11.62 lbs/force	Pull #13	12.52 lbs/force	Pull #14	13.89 lbs/force	Pull #15	14.64 lbs/force

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available.

TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

TSi Accreditation:

Erle Miles, III, Lab Director Testing Services (TSI) LLC

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0.

TSi is a certified independent testing laboratory by the Synthetic Turf Council



